

Independent Textile Testers

Test Number: 139876

Service, Inc.

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: American Fiber Cushion

August 19, 2013

Subject: Specimens of the submitted sample were prepared and tested in accordance with ASTM E 648-10 and/or Federal Test Method 372. NFPA 253

FLOORING RADIANT PANEL TEST

Sample Description

Ultra

Test Assembly

Mounted on 6mm FRC Board
(Using Premium Multi Purpose Adhesive)

<u>Test Results</u>	<u>Specimen No. 1</u>	<u>Specimen No. 2</u>	<u>Specimen No. 3</u>
Critical Radiant Flux	0.89 watts/cm ²	0.78 watts/cm ²	0.69 watts/cm ²
Total Burn Length	21.0 cm	26.0 cm	30.0 cm
Flame Front Out	26.0 minutes	21.0 minutes	20.0 minutes

Average Critical Radiant Flux

0.79 watts/cm²

Estimated Standard Deviation

0.10 watts/cm²

12.7% coefficient of variation



President L. Kent Suddeth

Independent Textile Testers

Test Number: 139876

Service, Inc.

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722

Phone: 706-278-3013

Fax: 706-272-7057

E-mail: info@ittslab.com

Test Report

Customer: American Fiber Cushion

August 19, 2013

Subject: "Consumer Product Safety Commission (CPSC) FF 1-70"
"16 CFR 1630"
"ASTM D 2859-96"
"Consumer Product Safety Improvement Act"

Scope: This test method covers the determination of the flammability of finished textile floor covering materials when exposed to an ignition source under controlled laboratory conditions. It is applicable to all types of textile floor coverings regardless of the method of fabrication or whether they are made from natural or man-made fibers.

FLAMMABILITY TEST REPORT

STYLE	COLOR	ROLL	TESTED	PASSED
Ultra	--	--	8	8

CPSIA

Consumer Product Safety
Commission Accredited
Laboratory: ID 1288



NVLAP[®]
NVLAP CODE 100166-0

This test report does not imply product certification, approval, or endorsement by NVLAP, NIST, or any agency of the Federal Government.

APPROVED
MEETS OR EXCEEDS
FEDERAL FLAMMABILITY
STANDARD CPSC FF 1-70

President L. Kent Suddeth